

DOBEL® F 105



APPLICATIONS

Film laminated sheet metal is used where the requirements are high regarding aesthetic and robust surfaces. **DOBEL® F 105** is especially suitable for interior applications. Typical uses are marine interiors such as wall and ceiling panels for cabins, bathrooms and showers, furniture and doors, but also for train interiors, office and shop fittings, apartment and detached house doors.

PRODUCT DESCRIPTION

DOBEL® F 105 consists of a 100 – 150µ thick Vinyl film laminated onto sheet metal. The base material is hot-dip galvanized steel or aluminium. The product is supplied with a removable protective film. A very wide range of single colours and printed patterns, such as woodgrain and textile, are available. The reverse side has as standard a primer coating, suitable for gluing and foaming.

DOBEL® F 105 is supplied as coils* or cut-to-length sheets. European standard EN 10169-1 for organic coated sheet is applicable for the product.

APPROVALS

DOBEL® F 105 laminated steel, is designed to be extremely flame resistant and generates very low amount of smoke, classified as surface material with low flame-spread characteristics.

DOBEL® F 105 is "CE" marked, approved and fulfills:
IMO 2010 FTP Code, Annex 1, Part 5 and Annex 2.
European Marine Directive 2014/90/EU

- Module B, EC Type Examination
- Module D, Quality System

American Bureau of Shipping-Manufacturing Assessment
SOLAS convention II-1/3-5, MSC.282(86), no content of asbestos.

DOBEL® F 105 aluminium also meets the criteria for the highest level of fire safety in accordance with EN 45545-2: 2013 requirements R1, HL3.

CLEANING & MAINTENANCE

With regular maintenance, your Metalcolour product will last even longer. Our product sheet "Maintenance Instructions" gives detailed instructions how to clean and maintain the product in best possible way.

STORAGE AND HANDLING

Care should be taken to avoid damage to the surface during handling and installation.

- Store in a clean dry place at room temperature (~23°C)
- Keep out of direct sunlight and away from heat sources
- Store the material in the original packaging
- Do not put heavy objects on top to prevent surface damage and pressure marks
- The protection film should not be removed until the material is installed

REACH & SUSTAINABILITY

Metalcolour Sverige AB continues to commit significant resources in order to ensure that our processes are increasingly environmentally friendly, performed under controlled conditions according to ISO 9001 and ISO 14001.

Metalcolour Sverige AB follows REACH regulations and uses no materials containing restricted chemicals on the SVHC candidate list, Substances of Very High Concern.

All of our products are compliant to RoHS Directive 2015/863.

Film laminated metal can be recovered at the end of its life cycle by remelting to new metal. **DOBEL® F 105** should be collected, as all other metal sheets, through the local scrap recovery channels.

TECHNICAL SERVICE AND INFORMATION

Dimensions and tolerances in the data sheet are standard. Other requirements available on agreement.

* Only available in steel.



PROPERTIES

| Specification | Data | Test method |
|----------------------|---------------------------|-------------|
| Film thickness | 100 – 150 µm | ISO 4591 |
| Min bending radius | Steel 0 T*/Aluminium 1 T* | |
| Adhesion | No remark | ISO 1520 |
| Impact resistance | 18 J | ISO 6272 |
| Max application temp | 60°C** | |

*T is the metal sheet thickness. **Temperatures exceeding 60°C may cause discolouration with time.

DIMENSIONS – SHEETS CUT TO SIZE

| Specification | Thickness (mm) | Width (mm) | Length (mm) | Zn thickness (g/m ² /side) |
|---------------|----------------|------------|-------------|---------------------------------------|
| Steel | 0.50 – 1.50 | – 1280 | – 3700 | 100*, 275 |
| Aluminium | 0.70 – 2.00 | – 1250 | – 3700 | |

* Standard Zn thickness. Maximum bundle weight: 3.0 tonnes (steel).

COILS

| Specification | Thickness (mm) | Width (mm) | Zn thickness (g/m ² /side) |
|---------------|----------------|------------|---------------------------------------|
| Steel | 0.50 – 1.00 | – 1280 | 100*, 275 |

* Standard Zn thickness. Inside diameter: 610 mm or 508 mm. Max coil weight: 5 tons.

TOLERANCES, STEEL/ALUMINIUM

| Thickness* (mm) | Tolerance (± mm) |
|------------------------------|------------------|
| 0.50 – 0.60 | 0.06 |
| 0.61 – 0.80 | 0.07 |
| 0.81 – 1.00 | 0.08 |
| 1.01 – 1.20 | 0.09 |
| 1.21 – 1.50 (Alu: 1.21-2.00) | 0.13 |

* According to SS – EN 10 143 (steel). According to EN 485 (aluminium).

| Dimensions | Tolerance (mm) |
|-------------|----------------|
| Width (mm) | -0/+6 |
| Length (mm) | -0/+2 |

There can be up to 5 mm naked edge (without film), on material with standard dimension tolerances.

Flatness: 5 mm standard deviation.

Straightness: 5 mm maximum deviation on a gauge length of 2000 mm.

Squareness: The squareness is expressed as the maximum allowable difference in length of diagonals. 3 mm up to length of 3000 mm.