



DOBEL® 2005

APPLICATIONS

Film laminated sheet metal is used where the requirements are high regarding aesthetic and robust surfaces. **DOBEL® 2005** is especially suitable for interior applications. Typical uses are marine interiors such as wall and ceiling panels for cabins, bathrooms and showers, furniture and doors, but also for train interiors, office and shop fittings, apartment and detached house doors.

PRODUCT DESCRIPTION

DOBEL® 2005 consists of a 115µ thick halogen free (PET) film laminated onto sheet metal. The base material is hot-dip galvanized steel. The product is supplied with a removable protective film. A range of single colours and printed patterns are available. The reverse side has as standard a primer coating, suitable for gluing and foaming.

DOBEL® 2005 is supplied as coils or cut-to-length sheets. European standard EN 10169-1 for organic coated sheet is applicable for the product.

MARINE APPROVALS

DOBEL® 2005 laminated steel, is designed to be extremely flame resistant and generates very low amount of smoke, classified as surface material with low flame-spread characteristics.

DOBEL® 2005 is "CE" marked, approved and fulfills:
IMO 2010 FTP Code, Annex 1, Part 5 and Annex 2.
European Marine Directive 2014/90/EU

- Module B, EC Type Examination
- Module D, Quality System

American Bureau of Shipping-Manufacturing Assessment SOLAS convention II-1/3-5, MSC.282(86), no content of asbestos

CLEANING OF SURFACE COATING

With regular maintenance, your Metalcolour product will last even longer. Our product sheet "Maintenance Instructions" gives detailed instructions how to clean and maintain the product in best possible way.

STORAGE AND HANDLING

Care should be taken to avoid damage to the surface during handling and installation.

- Store in a clean dry place at room temperature (~23°C)
- Keep out of direct sunlight and away from heat sources
- Store the material in the original packaging
- Do not put heavy objects on top to prevent surface damage and pressure marks
- The protection film should not be removed until the material is installed

REACH & SUSTAINABILITY

Metalcolour Sverige AB continues to commit significant resources in order to ensure that our processes are increasingly environmentally friendly, performed under controlled conditions according to ISO 9001 and ISO 14001.

Metalcolour Sverige AB follows REACH regulations and uses no materials containing restricted chemicals on the SVHC candidate list, Substances of Very High Concern.

All of our products are compliant to RoHS Directive 2015/863.

Film laminated metal can be recovered at the end of its life cycle by remelting to new metal. **DOBEL® 2005** should be collected, as all other metal sheets, through the local scrap recovery channels.

TECHNICAL SERVICE AND INFORMATION

Dimensions and tolerances in the data sheet are standard. Other requirements available on agreement.



PROPERTIES

Specification	Data	Test method
Film thickness	100 – 150 µm	ISO 4591
Min bending radius	1 T*	
Adhesion	No remark	ISO 1520
Max application temp	60°C**	ISO 6272

*T is the steel sheet thickness. **Temperatures exceeding 60°C may cause discolouration with time.

DIMENSIONS – SHEETS CUT TO SIZE

Specification	Thickness (mm)	Width (mm)	Length (mm)	Zn thickness (g/m ² /side)
Steel	0.50 – 1.50	– 1280	– 3700	100*, 275

* Standard Zn thickness. Maximum bundle weight: 3.0 tonnes.

COILS

Specification	Thickness (mm)	Width (mm)	Zn thickness (g/m ² /side)
Steel	0.50 – 1.00	– 1280	100*, 275

* Standard Zn thickness. Inside diameter: 610 mm or 508 mm. Max coil weight: 5 tons.

TOLERANCES, STEEL

Thickness* (mm)	Tolerance (± mm)
0.50 – 0.60	0.06
0.61 – 0.80	0.07
0.81 – 1.00	0.08
1.01 – 1.20	0.09
1.21 – 1.50	0.13

* According to SS – EN 10 143 (steel).

Dimensions	Tolerance (mm)
Width (mm)	-0/+6
Length (mm)	-0/+2

There can be up to 5 mm naked edge (without film), on material with standard dimension tolerances.

Flatness: 5 mm standard deviation.

Straightness: 5 mm maximum deviation on a gauge length of 2000 mm.

Squareness: The squareness is expressed as the maximum allowable difference in length of diagonals. 3 mm up to length of 3000 mm.