



DOBEL® FOODSAFE

APPLICATIONS

Film laminated sheet metal is used where the requirements are high regarding aesthetic and robust surfaces. **DOBEL® Foodsafe** can be used for wall and ceiling claddings in cold stores and food preparation areas. The material is also suitable as a facing material for sandwich panels in these areas.

PRODUCT DESCRIPTION

DOBEL® Foodsafe consists of a 120-200 µm thick Vinyl film laminated onto sheet metal. The base material is hot-dip galvanized steel or aluminium. The product is available in plain colours and is supplied with a removable protective film*. The reverse side has as standard a primer coating, suitable for gluing and foaming.

DOBEL® Foodsafe is supplied as coils** or cut-to-length sheets. European standard EN 10 169-1 for organic coated sheet is applicable for this product.

CLEANING & MAINTENANCE

With regular maintenance, your Metalcolour product will last even longer. Our product sheet "Maintenance Instructions" gives detailed instructions how to clean and maintain the product in best possible way.

STORAGE AND HANDLING

Care should be taken to avoid damage to the surface during handling and installation.

- Store in a clean dry place at room temperature (~23°C)
- Keep out of direct sunlight and away from heat sources
- Store the material in the original packaging
- Do not put heavy objects on top to prevent surface damage and pressure marks
- The protection film should not be removed until the material is installed

REACH & SUSTAINABILITY

Metalcolour Sverige AB continues to commit significant resources in order to ensure that our processes are increasingly environmentally friendly, performed under controlled conditions according to ISO 9001 and ISO 14001.

Metalcolour Sverige AB follows REACH regulations and uses no materials containing restricted chemicals on the SVHC candidate list, Substances of Very High Concern.

All of our products are compliant to RoHS Directive 2015/863.

Film laminated metal can be recovered at the end of its life cycle by remelting to new metal. **DOBEL® Foodsafe** should be collected, as all other metal sheets, through the local scrap recovery channels.

TECHNICAL SERVICE AND INFORMATION

Dimensions and tolerances in the data sheet are standard. Other requirements available on agreement.

* Not available on all types.

** Only available in steel.



PROPERTIES

| Specification | Data | Test method |
|----------------------|--------------|-------------|
| Film thickness | 120 – 200 µm | ISO 4591 |
| Min bending radius | 1 T* | |
| Adhesion | No remark | ISO 1520 |
| Impact resistance | 18 J | ISO 6272 |
| Max application temp | 60°C** | |

*T is the steel sheet thickness. ** Temperatures exceeding 60°C may cause discolouration with time.

DIMENSIONS – SHEETS CUT TO SIZE

| Specification | Thickness (mm) | Width (mm) | Length (mm) | Zn thickness (g/m ² /side) |
|---------------|----------------|------------|-------------|---------------------------------------|
| Steel | 0.50 – 1.50 | – 1280 | – 3700 | 100, 275* |
| Aluminium | 0.70 – 1.50** | – 1250 | – 3700 | |

* Standard Zn thickness. Maximum bundle weight: 3.0 tonnes (steel). ** 2,00 mm thickness available for min. order quantity of 7 tons.

COILS

| Specification | Thickness (mm) | Width (mm) | Zn thickness (g/m ² /side) |
|---------------|----------------|------------|---------------------------------------|
| Steel | 0.50 – 1.00 | – 1280 | 100, 275* |

* Standard Zn thickness. Inside diameter: 610 mm or 508 mm. Max coil weight: 5 tons.

TOLERANCES, STEEL/ALUMINIUM

| Thickness* (mm) | Tolerance (± mm) |
|------------------------------|------------------|
| 0.50 – 0.60 | 0.06 |
| 0.61 – 0.80 | 0.07 |
| 0.81 – 1.00 | 0.08 |
| 1.01 – 1.20 | 0.09 |
| 1.21 – 1.50 (Alu: 1.21-2.00) | 0.13 |

* According to SS – EN 10 143 (steel). According to EN 485 (aluminium).

| Dimensions | Tolerance (mm) |
|-------------|----------------|
| Width (mm) | -0/+6 |
| Length (mm) | -0/+2 |

There can be up to 5 mm naked edge (without film), on material with standard dimension tolerances.

Flatness: 5 mm standard deviation.

Straightness: 5 mm maximum deviation on a gauge length of 2000 mm.

Squareness: The squareness is expressed as the maximum allowable difference in length of diagonals. 3 mm up to length of 3000 mm.